


LR6-78HBD 390~420M

High Efficiency Low LID Bifacial PERC with Half-cut Technology

10-year Warranty for Materials and Processing; 30-year Warranty for Extra Linear Power Output



Complete System and Product Certifications

IEC 61215, IEC61730, UL1703

ISO 9001:2008: ISO Quality Management System

ISO 14001: 2004: ISO Environment Management System

TS62941: Guideline for module design gualification and type approval

OHSAS 18001: 2007 Occupational Health and Safety



* Specifications subject to technical changes and tests. LONGi Solar reserves the right of interpretation.



Front side performance equivalent to conventional low LID mono PERC:

- High module conversion efficiency (up to 19.3%)

- Better energy yield with excellent low irradiance performance and temperature coefficient - First year power degradation <2%

Bifacial technology enables additional energy harvesting from rear side (up to 25%)

Glass/glass lamination ensures 30 year product lifetime, with annual power degradation < 0.45%, 1500V compatible to reduce BOS cost

40mm frame design enables easy installation and robust mechanical strength

Solid PID resistance ensured by solar cell process optimization and careful module BOM selection

Reduced resistive loss with lower operating current


Higher energy yield with lower operating temperature


Reduced hot spot risk with optimized electrical design and lower operating current

Note: Due to continuous technical innovation, R&D and improvement, technical data above mentioned may be of modification accordingly. LONGi Solar have the sole right to make such modification at anytime without further notice; Demanding party shall request for the latest datasheet for such as contract need, and make it a consisting and binding part of lawful documentation duly signed by both parties.

LR6-78HBD 390~420M **Mechanical Parameters Operating Parameters**







Cell Orientation: 156 (6×26)	Operational Temperature: -40 °C ~ +85 °C			
Junction Box: IP67, three diodes	Power Output Tolerance: 0~+5 W			
Output Cable: 4mm ² , 300mm in length,	Vocand lsc Tolerance: ±3%			
length can be customized Glass: Dual glass	Maximum System Voltage: DC1500V (IEC/UL)			
2.0mm coated tempered glass	Maximum Series Fuse Rating: 20A			
Frame: Anodized aluminum alloy frame	Nominal Operating Cell Temperature: 45±2 C			
Weight: 29.0kg	Safety Class: Class II			
Dimension: 2180×996×40mm	Fire Rating: ULtype 3			
Packaging: 26pcs per pallet	0 //			
130pcs per 20'GP	Bifaciality: ≥75%			
520pcsper 40'HC				

Electrical Characteristics


													<u> </u>	
Model Number	LR6-78H	BD-390M	LR6-78H	BD-395M	LR6-78H	BD-400M	LR6-78H	BD-405M	LR6-78H	BD-410M	LR6-78HI	BD-415M	LR6-78H	3D-420N
Testing Condition	STC	NOCT	STC	NOCT	STC	NOCT								
Maximum Power (Pmax/W)	390	290.0	395	293.7	400	297.4	405	301.1	410	304.9	415	308.6	420	312.3
Open Circuit Voltage (Voc/V)	51.9	48.4	52.1	48.6	52.4	48.8	52.6	49.0	52.8	49.2	53.0	49.4	53.2	49.6
Short Circuit Current (lsc/A)	9.74	7.89	9.82	7.95	9.88	8.00	9.95	8.06	10.02	8.11	10.10	8.18	10.18	8.24
Voltage at Maximum Power (Vmp/V)	43.4	40.3	43.6	40.5	43.8	40.7	44.0	40.8	44.2	41.0	44.4	41.2	44.6	41.4
Current at Maximum Power (Imp/A)	8.99	7.20	9.06	7.26	9.14	7.32	9.21	7.38	9.29	7.44	9.35	7.49	9.42	7.54
Module Efficiency(%)	18	3.0	18	8.2	18	3.4	18	3.7	1	8.9	19	9.1	19	9.3
STC (Standard Testing Conditions): Irradiance 1000W/m ² , Cell Temperature 25 °C , Spectra at AM1.5														
NOCT (Nominal Operating Cell Temperature): Irradiance 800W/m², Ambient Temperature 20 C, Spectra at AM1.5, Wind at 1m/S														

Electrical characteristics with different rear side power gain (reference to 400W front)


Pmax /W	Voc/V	lsc /A	Vmp/V	Imp /A	Pmax gain
420	52.4	10.37	43.8	9.60	5%
440	52.4	10.87	43.8	10.05	10%
460	52.5	11.36	43.9	10.51	15%
480	52.5	11.86	43.9	10.97	20%
500	52.5	12.35	43.9	11.43	25%

Temperature Ratings (STC)		Mechanical Loading			
Temperature Coefficient of Isc	+0.060%/°C	Front Side Maximum Static Loading	5400Pa		
Temperature Coefficient of Voc	-0.300%/°C	Rear Side Maximum Static Loading	2400Pa		
Temperature Coefficient of Pmax	-0.370%/ °C	Hailstone Test	25mm Hailstone at the speed of 23m/s		

I-V Curve








Current-Voltage Curve (LR6-78HBD-400M)

Test uncertainty for Pmax: ±3%



Note: Due to continuous technical innovation, R&D and improvement, technical data above mentioned may be of modification accordingly. LONGi Solar have the sole right to make such modification at anytime without further notice; Demanding party shall request for the latest datasheet for such as contract need, and make it a consisting and binding part of lawful documentation duly signed by both parties.